


MM / RM Chip Breaker

MM
Chip Breaker
(Medium cutting)



RM
Chip Breaker
(Rough cutting)

Turning Chip breaker for Stainless Steel

- **Increased Productivity**
Extended tool life at high speeds, feeds, and depths of cut
- **Comprehensive Use**
A wide Chip Breaker lineup for most workpiece sizes and types, including heavy interruption
- **Solutions for Most Common Issues in Stainless Steel Machining**
Prevents built-up edge, notch wear, plastic deformation, and burr creation



High-performance Turning Grade and Chip Breaker for Austenitic, Martensitic, and Ferritic Stainless Steel

Stainless steels can be roughly divided into three types - the austenite, the martensite and the ferrite. They feature smooth surfaces and excellent corrosion resistance. Their use typically requires no need for surface paints or colors. The most commonly used stainless steels are high hardness types such as 13Cr, 18Cr, 18Cr-8Ni, etc.



MM Chip Breaker

Medium cutting





RM Chip Breaker

Rough cutting

The reason Stainless Steel is often considered a hard-to-cut material is its large shearing resistance that can easily cause work hardening, built-up edges, and edge fracture. Its combination of tough and hard material characteristics require the prudent selection of grades and chip breakers.

The MM chip breaker for medium cutting is the 1st recommended for stainless steel. Its dual angle land design allows for both sharp cutting performance and strong cutting edges, which promotes extended tool life and minimized cutting force and built-up edge. In addition, wide chip pockets prevent chips from interrupting the minor cutting edges and instead lets the chips out of the cutting area. These chip breaker features help prevent plastic deformation and excessive wear.

The RM chip breaker for roughing is recommended in rough machining and in cases where burrs are an issue. It has a wide land and rake angle lowering cutting resistance. Cutting heats can flow around the gentle slope of rake surface and can be effectively dispersed and evacuated at high feeds and high depths of cut.




MM Chip Breaker (For medium cutting)

M

- The 1st recommended chip breaker for stainless steel machining
- Sharp cutting performance and insert toughness achieved by the use of a dual land
- Wide chip pockets for stable chip evacuation at high feeds/depths of cut

MM Chip Breaker Features



Variable Land

- Excellent chip control and sharp cutting at low depths of cut
- Delays crater wear
- Prevents plastic deformation

Dual Land

- Balance between requirements of sharp and tough cutting edges
- Sharp cutting edge for high speed machining
- Prevents chipping in interrupted machining

Wide Chip Pocket

- Stable chip evacuation at high speeds/feeds
- Improved surface finishes by reduced workpiece scratches caused by work-hardened chips at high depths of cut
- Prevents built-up edge

Low Cutting Force at 100° corner

- 100° corner angle is recommended for roughing outer diameters and preventing burrs
- Reduced cutting load for high feed machining

[Chip Breaker Code]

MM


Workpiece range

- P : Steel
- **M : Stainless Steel**
- K : Cast iron


Application range

- F : Finish
- **M : Medium**
- R : Rough

Application Range



Recommended Cutting Range



Recommended Cutting Conditions

Application	Chip breaker	Recommended Cutting conditions					
		Depth of cut, ap (mm)			Feed, fn (mm/rev)		
		Min.	REC	Max.	Min.	REC	Max.
Medium cutting	MM	0.5	3.0	5.5	0.12	0.25	0.45


RM Chip Breaker (For rough cutting)

M

- The 1st recommended chip breaker for rough and interrupted machining of stainless steel
- Prevents notch wear and burrs at high feeds and depths of cut
- Reduced cutting force extends tool life in high feed machining


RM Chip Breaker Features

Variable Land



- Excellent chip control and sharp cutting at low depths of cut
- Delays crater wear
- Prevents plastic deformation


Wide Land & Gentle Front Angle



- Sharp cutting edges and wide land reduce cutting force
- Reduced burrs
- Dispersed cutting load enables higher toughness

Stepped Design

- Stepped design makes chip evacuation easier
- Smooth chip evacuation prevents plastic deformation



Low Cutting Force at 100° corner

- 100° corner angle is recommended for roughing outer diameters and preventing notch wear
- Stepped design reduces cutting load

[Chip Breaker Code]

R M


Workpiece range

- P : Steel
- **M : Stainless Steel**
- K : Cast iron


Application range

- F : Finish
- M : Medium
- **R : Rough**

Application Range



Recommended Cutting Range



Recommended Cutting Conditions

Application	Chip breaker	Recommended Cutting conditions					
		Depth of cut, a_p (mm)			Feed, f_n (mm/rev)		
		Min.	REC	Max.	Min.	REC	Max.
Rough cutting	RM	2.0	4.0	6.0	0.15	0.3	0.55



➤ Cutting Performance

• A gentle slope of MM chip breaker **minimizes built-up edge**

• Improved surface finish and chip control from inhibited built-up edges

Built-up edge

- Workpiece X6CrAl13 (Ferrite)
- Cutting conditions $vc(m/min) = 180$, $fn(mm/rev) = 0.3$, $ap(mm) = 3.0$, wet
- Tools Insert CNMG120408-MM (NC9125) Holder PCLNL2525-M12




• A wide land and rake angle of RM chip breaker **disperse cutting loads and prevents notch wear**

• Improved surface finish and reduced burrs by preventing notch wear

Notch wear

- Workpiece X12Cr13 (Martensite)
- Cutting conditions $vc(m/min) = 150$, $fn(mm/rev) = 0.25$, $ap(mm) = 3.0$, wet
- Tools Insert CNMG120408-RM (NC9115) Holder PCLNL2525-M12





• The MM chip breaker promptly dissipates the concentrated cutting edge heat to **prevent plastic deformation** during machining

• Less vibration and cutting load due to reduced plastic deformation

Plastic deformation

- Workpiece X5CrNiMo17-12-2 (Austenite)
- Cutting conditions $vc(m/min) = 200$, $fn(mm/rev) = 0.35$, $ap(mm) = 2.0$, dry
- Tools Insert CNMG120408-MM (NC9135) Holder PCLNL2525-M12





• The wide land and rake angle of the RM chip breaker **improves cutting performance and prevents burrs**

• Improved chip control improves surface finish and extends tool life

Burr

- Workpiece Duplex
- Cutting conditions $vc(m/min) = 120$, $fn(mm/rev) = 0.2$, $ap(mm) = 2.0$, dry
- Tools Insert CNMG120408-RM (NC9125) Holder PCLNL2525-M12



➔ Recommended Grade and Chip Breaker per Stainless Steel Type

• Machinability is related to the type of stainless steel.

• The Ferritic and the Martensite types are more machinable.

• The Duplex and PH types are the most difficult type to machine.

Austenitic Stainless Steel

- Heavy work hardening (Edge chipping accelerates wear)
- Poor heat conductivity (Three times lower than carbon steel → Increase in cutting area temperature)
- High ductility (Strong chance for deformation at high temperature → Long chips or tough chips occurs)
- Type : X10CrNiS18-9, X5CrNi18-9, X5CrNiMo17-12-2 etc.

Coated	Grade	Cutting speed, vc(m/min)					Continuous	Low interrupted	High interrupted
		50	100	150	200	250			
CVD	NC9115			160	220		MM / RM	MM	-
	NC9125			150	200		MM / RM	MM / RM	RM
	NC9135		100	150			MM / RM	MM / RM	RM
PVD	PC8115			140	180		MM / RM	MM / RM	RM
	PC5300		100	160			MM / RM	MM / RM	RM

Ferritic / Martensitic Stainless Steel

- Strong chance for work hardening at high temperature (Crater wear is promoted)
- High toughness through tempering and annealing (Long chips are easily created)
- High carbon contents increase its hardness)
- Type : X20Cr13, X12Cr13, X12CrS13, X70CrMo15 etc.

Coated	Grade	Cutting speed, vc(m/min)					Continuous	Low interrupted	High interrupted
		50	100	150	200	250			
CVD	NC9115			150	250		MM / RM	MM	-
	NC9125			120	220		MM / RM	MM / RM	RM
	NC9135		100	150			MM / RM	MM / RM	RM
PVD	PC8115			140	220		MM / RM	MM / RM	RM
	PC5300		120	200			MM / RM	MM / RM	RM

Duplex Stainless Steel

- Its presence of both austenitic and ferritic fine matrix requires both types of cutting characteristics for each material's attribute.
- One of the most hard to cut stainless steels as its higher yield strength makes chip control harder than the Austenite
- Type : FeMn35Cr20Cu4Mo2*, X2CrNiMoN22.5.3*, X2CrNiMoN25.7.4*


Coated	Grade	Cutting speed, vc(m/min)					Continuous	Low interrupted	High interrupted
		50	100	150	200	250			
CVD	NC9115			120	160		MM / RM	MM	-
	NC9125			100	140		MM / RM	MM / RM	RM
	NC9135		60	100			MM / RM	MM / RM	RM
PVD	PC8115		85	140			MM / RM	MM / RM	RM
	PC5300		80	120			MM / RM	MM / RM	RM

Precipitation Hardened(PH) Stainless Steel

- High tensile strength (2 times higher than other stainless steels) increases cutting load
- Low heat conductivity cause cutting edge damage from high temp chips
- Type : X5CrNiCuNb16-4, X7CrNiAl17-7

Coated	Grade	Cutting speed, vc(m/min)					Continuous	Low interrupted	High interrupted
		50	100	150	200	250			
CVD	NC9115		50	110			MM / RM	MM	-
	NC9125		40	110			MM / RM	MM / RM	RM
	NC9135		30	100			MM / RM	MM / RM	RM
PVD	PC8115		30	80			MM / RM	MM / RM	RM
	PC5300		35	90			MM / RM	MM / RM	RM

Grade Lineup



Chip Removal Volume per Cutting Speed

Grade	ISO	Cutting speed (m/min)	Chip removal volume(cm ³)
NC9135	M35	150	212
PVD coated grade	M30		256
Competitor	M35		126
NC9135	M35	200	126
PVD coated grade	M30		56
Competitor	M35		66

→ Higher productivity than PVD grades at high speeds over 150m/min

- The NC9100 Series CVD coated grades are differentiated from PVD grades by their application range
- Compared to PVD coated grades with similar substrates, CVD coated ones have longer tool life over the PVD, in large scale rough machining at high speeds or in high temperature conditions
- The NC9115 / NC9125 / NC9135 grades are provided according to the degree of interruption or vibration during machining

Turning Grade Comparison Chart for Stainless Steel

Coated	ISO	KORLOY	Competitor A	Competitor B	Competitor C	Competitor D	Competitor E	Competitor F	Competitor G
CVD	M15	NC9115	TT9215	GC2015	CA6515	MC7015	TM2000	WAM10	AC610M
	M25	NC9125	TT9225	GC2025	CA6525	MC7025	TM4000	WAM20	AC6030M
	M35	NC9135	TT9235	GC235	-	US735	-	WAM30	AC630M
PVD	M15	PC8115	-	GC1115	PR1025	VP20RT	CP200	WSM20	-
	M30	PC5300	TT9080	GC2035	PR1125	MP7035	CP500	WSM30	AC6040M

Turning Chip Breaker Comparison Chart for Stainless Steel (Negative type)

Application	KORLOY	Competitor A	Competitor B	Competitor C	Competitor D	Competitor E	Competitor F	Competitor G
Rough cutting	RM	ET	MR	MU	RM	M5	NR7	MU
Medium cutting	MM	EM	MM	MS	MM	MF3	NM4	GU
Finish cutting	-	EA	MF	-	LM	MF1	NS4	SU

Turning Chip Breaker Comparison Chart for Stainless Steel (Positive type)

Application	KORLOY	Competitor A	Competitor B	Competitor C	Competitor D	Competitor E	Competitor F	Competitor G
Medium cutting	MP	PC, MT	MM	HQ	MV	MF2	PS5	MU
Finish cutting	VL	FA	MF	MQ	FV	FF1	PF4	SU

⇒ Application Examples




Hydraulics part (Mechanical seal)

- Workpiece X5CrNi18-9
- Cutting conditions $vc(m/min) = 140$, $fn(mm/rev) = 0.28$, $ap(mm) = 3.0$, wet
- Tools Insert CNMG120408-MM (NC9125)
Holder S32S-PCLCR-12

MM (NC9125) **9ea/edge**
Competitor A (M25) 5ea/edge

80% more

➔ Stable chip evacuation reduces cutting load and plastic deformation, which increases tool life 80% longer tool life than competitor A (M25)



Valve part (Piston valve)

- Workpiece X5CrNi18-9 (Solution treatment)
- Cutting conditions $vc(m/min) = 140$, $fn(mm/rev) = 0.28$, $ap(mm) = 3.0$, wet
- Tools Insert CNMG120408-MM (NC9125)
Holder DCLNL2525-M12

MM (NC9125) **5ea/edge**
Competitor B (M25) 2ea/edge

150% more

➔ Dual land design combines sharp cutting performance and high toughness in high hardness machining 150% longer tool life than competitor B (M25)



Wind power/offshore plant part (Flange)

- Workpiece X6CrNiNb18-10* (Outer diameter roughing)
- Cutting conditions $vc(m/min) = 150$, $fn(mm/rev) = 0.3\sim 0.5$, $ap(mm) = 4.0\sim 6.0$, wet
- Tools Insert CNMG160616-MM (NC9125)
Holder PCLNR3232-P16

MM (NC9125) **15ea/edge**
Competitor C (M25) 10ea/edge

50% more

➔ 50% longer tool life than competitor C (M25)



Wind power/offshore plant part (Flange)

- Workpiece X6CrNiNb18-10* (Inner diameter finishing)
- Cutting conditions $vc(m/min) = 175$, $fn(mm/rev) = 0.45$, $ap(mm) = \sim 1.0$, wet
- Tools Insert SNMG190616-MM (NC9125)
Holder S50U-PCLCR-19

MM (NC9125) **12ea/edge**
Competitor D (M25) 8ea/edge

50% more

➔ 50% longer tool life than competitor D (M25)

* Germany [DIN]

⇒ Application Examples



Wind power plant part (Flange)

- Workpiece X5CrNiMo17-12-2
- Cutting conditions $vc(m/min) = 175$, $fn(mm/rev) = 0.3\sim 0.8$, $ap(mm) = 0.5$, wet
- Tools
Insert TNMG220416-RM (NC9135)
Holder PTFNR3232-P22

RM (NC9135) 5ea/edge
Competitor E (M35) 2ea/edge

150% more

➔ **Extended tool life from improved chipping resistance and reduced built-up edge
150% longer tool life than competitor E (M35)**



Plant part (Flange)

- Workpiece Super Duplex
- Cutting conditions $vc(m/min) = 100$, $fn(mm/rev) = 0.5$, $ap(mm) = 3$, wet
- Tools
Insert CNMG160616-MM (NC9125)
Holder PCLNR3232-P16

MM (NC9125) 12ea/edge
Competitor F (M25) 8ea/edge

50% more

➔ **Extended tool life from inhibited wear and chipping
50% longer tool life than competitor F (M25)**



Hydraulics part

- Workpiece Duplex
- Cutting conditions $vc(m/min) = 120$, $fn(mm/rev) = 0.4$, $ap(mm) = 6$, wet
- Tools
Insert CNMG160616-RM (NC9125)
Holder DCLNR3232-P16

RM (NC9125) 7ea/edge
Competitor G (M25) 5ea/edge

40% more

➔ **Improved blade stability compared to competitor's
40% longer tool life than competitor G (M25)**



Machinery part






- Workpiece X5CrNi18-9
- Cutting conditions $vc(m/min) = 180$, $fn(mm/rev) = 0.4$, $ap(mm) = 1.5$, wet
- Tools
Insert CNMG120408-MM (NC9125)
Holder DCLNL2525-M12

MM (NC9125) 6ea/edge
VM (PC9030) 3ea/edge

100% more








➔ **Extended tool life from superior resistance to built-up edge and wear compared to PC9030
100% higher productivity than PC9030 under higher cutting conditions**

Available Stock [Negative type]

Shape	Designation	Coated					Dimensions(mm)					Cutting conditions	
		NC9115	NC9125	NC9135	PC5300	PC8115	l	d	t	r	d ₁	Feed, fn(mm/rev)	Depth of cut, ap(mm)
Medium cutting 	CNMG	090308-MM					8.8	9.525	3.18	0.8	3.81	0.10 ~ 0.40	0.50 ~ 5.00
		120404-MM	●	●	●	●	12.4	12.7	4.76	0.4	5.16	0.10 ~ 0.40	0.50 ~ 5.50
		120408-MM	●	●	●	●	12.0	12.7	4.76	0.8	5.16	0.12 ~ 0.45	0.50 ~ 5.50
		120412-MM	●	●	●	●	11.6	12.7	4.76	1.2	5.16	0.15 ~ 0.60	0.50 ~ 5.50
		120416-MM	●	●	●	●	11.2	12.7	4.76	1.6	5.16	0.20 ~ 0.65	0.50 ~ 5.50
		160608-MM	●	●	●	●	15.3	15.875	6.35	0.8	6.35	0.12 ~ 0.45	0.50 ~ 7.00
		160612-MM	●	●	●	●	14.8	15.875	6.35	1.2	6.35	0.15 ~ 0.60	0.50 ~ 7.00
		160616-MM	●	●	●	●	14.4	15.875	6.35	1.6	6.35	0.18 ~ 0.65	0.50 ~ 7.00
		190608-MM	●	●	●	●	18.5	19.05	6.35	0.8	7.93	0.12 ~ 0.45	0.50 ~ 8.50
		190612-MM	●	●	●	●	18.1	19.05	6.35	1.2	7.93	0.15 ~ 0.60	0.50 ~ 8.50
190616-MM	●	●	●	●	17.7	19.05	6.35	1.6	7.93	0.18 ~ 0.65	0.50 ~ 8.50		
Rough cutting 	CNMG	120404-RM	●	●	●	●	12.4	12.7	4.76	0.4	5.16	0.10 ~ 0.50	2.00 ~ 6.00
		120408-RM	●	●	●	●	12.0	12.7	4.76	0.8	5.16	0.15 ~ 0.55	2.00 ~ 6.00
		120412-RM	●	●	●	●	11.6	12.7	4.76	1.2	5.16	0.20 ~ 0.60	2.00 ~ 6.00
		120416-RM	●	●	●	●	11.2	12.7	4.76	1.6	5.16	0.25 ~ 0.70	2.00 ~ 6.00
		160608-RM	●	●	●	●	15.3	15.875	6.35	0.8	6.35	0.15 ~ 0.55	2.00 ~ 8.00
		160612-RM	●	●	●	●	14.8	15.875	6.35	1.2	6.35	0.20 ~ 0.60	2.00 ~ 8.00
		160616-RM	●	●	●	●	14.4	15.875	6.35	1.6	6.35	0.25 ~ 0.70	2.00 ~ 8.00
		190608-RM	●	●	●	●	18.5	19.05	6.35	0.8	7.93	0.15 ~ 0.55	2.00 ~ 10.00
		190612-RM	●	●	●	●	18.1	19.05	6.35	1.2	7.93	0.20 ~ 0.60	2.00 ~ 10.00
		190616-RM	●	●	●	●	17.7	19.05	6.35	1.6	7.93	0.25 ~ 0.70	2.00 ~ 10.00
250924-RM					23.3	25.40	9.52	2.4	9.12	0.40 ~ 1.20	4.00 ~ 14.00		
Medium cutting 	DNMG	110408-MM					10.8	9.525	4.76	0.8	3.81	0.10 ~ 0.40	0.50 ~ 5.00
		150404-MM	●	●	●	●	15.1	12.7	4.76	0.4	5.16	0.10 ~ 0.40	0.50 ~ 6.40
		150408-MM	●	●	●	●	14.7	12.7	4.76	0.8	5.16	0.12 ~ 0.45	0.50 ~ 6.40
		150412-MM	●	●	●	●	14.4	12.7	4.76	1.2	5.16	0.15 ~ 0.60	0.50 ~ 6.40
		150604-MM	●	●	●	●	15.1	12.7	6.35	0.4	5.16	0.10 ~ 0.40	0.50 ~ 6.40
		150608-MM	●	●	●	●	14.7	12.7	6.35	0.8	5.16	0.12 ~ 0.45	0.50 ~ 6.40
150612-MM	●	●	●	●	14.4	12.7	6.35	1.2	5.16	0.15 ~ 0.60	0.50 ~ 6.40		
Rough cutting 	DNMG	150404-RM	●	●	●	●	15.1	12.7	4.76	0.4	5.16	0.10 ~ 0.50	2.00 ~ 6.00
		150408-RM	●	●	●	●	14.7	12.7	4.76	0.8	5.16	0.15 ~ 0.55	2.00 ~ 6.00
		150412-RM	●	●	●	●	14.4	12.7	4.76	1.2	5.16	0.20 ~ 0.60	2.00 ~ 6.00
		150604-RM	●	●	●	●	15.1	12.7	6.35	0.4	5.16	0.10 ~ 0.50	2.00 ~ 6.00
		150608-RM	●	●	●		14.7	12.7	6.35	0.8	5.16	0.15 ~ 0.55	2.00 ~ 6.00
150612-RM	●	●	●		14.4	12.7	6.35	1.2	5.16	0.20 ~ 0.60	2.00 ~ 6.00		
Medium cutting 	SNMG	090308-MM					8.7	9.525	3.18	0.8	3.81	0.10 ~ 0.40	0.50 ~ 5.00
		120404-MM	●	●	●	●	12.3	12.7	4.76	0.4	5.16	0.10 ~ 0.40	0.50 ~ 6.40
		120408-MM	●	●	●	●	11.9	12.7	4.76	0.8	5.16	0.12 ~ 0.45	0.50 ~ 6.40
		120412-MM	●	●	●	●	11.5	12.7	4.76	1.2	5.16	0.15 ~ 0.60	0.50 ~ 6.40
		120416-MM					11.1	12.7	4.76	1.6	5.16	0.18 ~ 0.65	0.50 ~ 6.40
		150608-MM					15.0	15.875	6.35	0.8	6.35	0.12 ~ 0.45	0.50 ~ 8.00
		150612-MM	●	●	●	●	14.6	15.875	6.35	1.2	6.35	0.15 ~ 0.60	0.50 ~ 8.00
		150616-MM					14.2	15.875	6.35	1.6	6.35	0.18 ~ 0.65	0.50 ~ 8.00
		190608-MM	●	●	●	●	18.0	19.05	6.35	0.8	7.93	0.12 ~ 0.45	0.50 ~ 9.50
		190612-MM	●	●	●	●	17.8	19.05	6.35	1.2	7.93	0.15 ~ 0.60	0.50 ~ 9.50
190616-MM					17.4	19.05	6.35	1.6	7.93	0.18 ~ 0.65	0.50 ~ 9.50		

● : Managed stock

Available Stock [Negative type]

Shape	Designation		Coated					Dimensions(mm)					Cutting conditions	
			NC9115	NC9125	NC9135	PC5300	PC8115	l	d	t	r	d ₁	Feed, fn(mm/rev)	Depth of cut, ap(mm)
Rough cutting 	SNMG	120404-RM	●	●	●	●	●	12.3	12.7	4.76	0.4	5.16	0.10 ~ 0.50	2.00 ~ 6.00
		120408-RM	●	●	●	●	●	11.9	12.7	4.76	0.8	5.16	0.15 ~ 0.55	2.00 ~ 6.00
		120412-RM		●	●	●	●	11.5	12.7	4.76	1.2	5.16	0.20 ~ 0.60	2.00 ~ 6.00
		120416-RM						11.1	12.7	4.76	1.6	5.46	0.25 ~ 0.70	2.00 ~ 6.00
		150612-RM		●	●	●	●	14.6	15.875	6.35	1.2	6.35	0.20 ~ 0.60	2.00 ~ 8.00
		190608-RM		●	●	●	●	18.0	19.05	6.35	0.8	7.93	0.20 ~ 0.60	2.00 ~ 10.00
		190612-RM		●	●	●	●	17.8	19.05	6.35	1.2	7.93	0.20 ~ 0.60	2.00 ~ 10.00
		190616-RM						17.4	19.05	6.35	1.6	7.93	0.25 ~ 0.70	2.00 ~ 10.00
		250924-RM						23.0	25.4	9.52	2.4	9.12	0.40 ~ 1.20	4.00 ~ 14.00
Medium cutting 	TNMG	160404-MM	●	●	●	●	●	15.5	9.525	4.76	0.4	3.81	0.10 ~ 0.40	0.50 ~ 4.80
		160408-MM	●	●	●	●	●	14.5	9.525	4.76	0.8	3.81	0.12 ~ 0.45	0.50 ~ 4.80
		160412-MM						13.5	9.525	4.76	1.2	3.81	0.15 ~ 0.60	0.50 ~ 4.80
		160416-MM						12.5	9.525	4.76	1.6	3.81	0.18 ~ 0.65	0.50 ~ 4.80
		220404-MM						21.0	12.7	4.76	0.4	5.16	0.10 ~ 0.40	0.50 ~ 6.50
		220412-MM		●	●	●	●	19.0	12.7	4.76	1.2	5.16	0.15 ~ 0.60	0.50 ~ 6.50
Rough cutting 	TNMG	160404-RM	●	●	●	●	●	15.5	9.525	4.76	0.4	3.81	0.10 ~ 0.50	2.00 ~ 5.50
		160408-RM	●	●	●	●	●	14.5	9.525	4.76	0.8	3.81	0.15 ~ 0.55	2.00 ~ 5.50
		160412-RM						13.5	9.525	4.76	1.2	3.81	0.20 ~ 0.60	2.00 ~ 5.50
		220408-RM		●	●	●	●	20.0	12.7	4.76	0.8	5.16	0.15 ~ 0.55	2.00 ~ 7.50
		220412-RM		●	●	●	●	19.0	12.7	4.76	1.2	5.16	0.20 ~ 0.60	2.00 ~ 7.50
Medium cutting 	VNMG	160404-MM		●	●	●	●	15.6	9.525	4.76	0.4	3.81	0.10 ~ 0.40	0.50 ~ 4.00
		160408-MM		●	●	●	●	14.6	9.525	4.76	0.8	3.81	0.12 ~ 0.45	0.50 ~ 4.00
		160412-MM						13.6	9.525	4.76	1.2	3.81	0.15 ~ 0.60	0.50 ~ 4.00
Rough cutting 	VNMG	160404-RM						15.6	9.525	4.76	0.4	3.81	0.10 ~ 0.50	2.00 ~ 5.00
		160408-RM						14.6	9.525	4.76	0.8	3.81	0.15 ~ 0.55	2.00 ~ 5.00
		160412-RM						13.6	9.525	4.76	1.2	3.81	0.20 ~ 0.60	2.00 ~ 5.00
Medium cutting 	WNMG	060408-MM						6.1	9.525	4.76	0.8	3.81	0.10 ~ 0.40	0.50 ~ 4.00
		060412-MM						6.0	9.525	4.76	1.2	3.81	0.12 ~ 0.45	0.50 ~ 4.00
		080404-MM		●	●	●	●	8.4	12.7	4.76	0.4	5.16	0.10 ~ 0.40	0.50 ~ 4.00
		080408-MM	●	●	●	●	●	8.3	12.7	4.76	0.8	5.16	0.12 ~ 0.45	0.50 ~ 4.00
		080412-MM	●	●	●	●	●	8.2	12.7	4.76	1.2	5.16	0.15 ~ 0.60	0.50 ~ 4.00
Rough cutting 	WNMG	060404-RM						6.2	9.525	4.76	0.4	3.81	0.10 ~ 0.50	1.50 ~ 3.00
		060408-RM						6.1	9.525	4.76	0.8	3.81	0.15 ~ 0.55	1.50 ~ 3.00
		060412-RM						6.0	9.525	4.76	1.2	3.81	0.20 ~ 0.60	1.50 ~ 3.00
		080404-RM		●	●	●	●	8.4	12.7	4.76	0.4	5.16	0.10 ~ 0.50	2.00 ~ 4.00
		080408-RM	●	●	●	●	●	8.3	12.7	4.76	0.8	5.16	0.15 ~ 0.55	2.00 ~ 4.00
		080412-RM	●	●	●	●	●	8.2	12.7	4.76	1.2	5.16	0.20 ~ 0.60	2.00 ~ 4.00

● : Managed stock

www.korloy.com



KORLOY

Holystar B/D, 1350, Nambusunhwan-ro, Geumcheon-gu, Seoul, 08536, Korea

Tel : +82-2-522-3181 Fax : +82-2-522-3184, +82-2-3474-4744 Web : www.korloy.com E-mail : export@korloy.com



KORLOY AMERICA

620 Maple Avenue, Torrance, CA 90503, USA

Tel : +1-310-782-3800 Toll Free : +1-888-711-0001 Fax : +1-310-782-3885
www.korloyamerica.com E-mail : sales@korloy.us



KORLOY EUROPE

Gablonzer Str. 25-27, 61440 Oberursel, Germany

Tel : +49-6171-277-83-0 Fax : +49-6171-277-83-59
www.korloyeurope.com E-mail : sales@korloyeurope.com



KORLOY INDIA

Plot NO.415, Sector 8, IMT Manesar, Gurgaon 122051, Haryana, INDIA

Tel : +91-124-4391790 Fax : +91-124-4050032
www.korloyindia.com E-mail : sales.kip@korloy.com



KORLOY BRASIL

Av. Aruana 280, conj.12, WLC, Alphaville, Barueri,
CEP06460-010, SP, Brasil

Tel : +55-11-4193-3810 E-mail : vendas@korloy.com